

Slip Check to AS 4586-2013

RevoDeck™ Solid Composite Decking (S Range)

Report Number: R36377

Report Date: 15 October 2026

Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

Issued by

Safe Environments Pty Limited
6/7 Inglewood Place
Norwest NSW 2153

Prepared for

First Class Decking & Timbers Pty Ltd
Po Box 3651
Success WA 6964

Approved by



Carl Strautins
Authorised Signatory

15 October 2026

Test Report No. R36377

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by: First Class Decking & Timbers Pty Ltd
Client Address: Po Box 3651
Success WA 6964
Product Manufacturer: Supplied by First Class Decking & Timbers Pty Ltd
Product Description: RevoDeck™ Solid Composite Decking (S Range)

Test conducted according to: AS 4586:2013 Appendix A
Sampling Procedures: Performed by client and tested as received.
Location: 6/7 Inglewood Place, Norwest NSW 2153

Conducted by: Nathan Vanderburg

Date: 14 October 2026
Sample: Unfixed
Rubber slider used: Slider 96
Slope of specimen: Tested on a flat level surface
Direction of Test: Parallel to wood-like grain
Temperature: 19°C
Cleaning: None
Conditioned: Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	30	29	32	32	29

Reported SRV of Sample:	30
Class:	P2

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.